

CERAN XM 460



Grease



Extreme-pressure water resistant high temperature **“NEW GENERATION”** calcium sulfonate complex grease

APPLICATIONS

Multi purpose heavy duty water resistant grease.
Shock loaded applications in industry even in severe demanding environment (water, dust, high temperature).

- **CERAN XM 460** is made of the **NEW GENERATION** calcium sulfonate complex soap designed by TOTAL Lubrifiants. This new soap has enhanced properties in terms of water and thermal resistance, load capacity, anticorrosion properties while keeping a very high level of pumpability and ability to lubricate well in case of high loads.
- **CERAN XM 460** is suitable for the lubrication of all kinds of components subject to high loads and temperatures, shocks, working in conditions where the grease is in frequent contact with water (even sea water due to enhanced antirust performances).
- **CERAN XM 460** is suitable for the lubrication of **bearings in steel plants** (continuous castings and rolling mills) and in **paper industry**. **Ceran XM 460** is also suitable for the lubrication of hard wood **granular presses** and in all industrial applications under severe conditions (wet, loaded, high temperature, dust,...) namely **mining and cement industries**.
- **CERAN XM 460** is suitable for use in centralized greasing systems.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system.

SPECIFICATIONS

- ISO 6743-9: L-XBFB 1/2
- DIN 51 502: KP1/2R -25

ADVANTAGES

True multi purpose.
Shock loads.
Water resistant.
Anti corrosion.

NEW GENERATION
allowing use in high speed factors.

No harmful substances.

- The **NEW GENERATION** of calcium sulfonate complex soap developed by TOTAL Lubrifiants allows **CERAN XM 460** to present outstanding performances even at high nDm. This **NEW GENERATION** keeps all benefits in terms of corrosion protection, bearings lifetime, high loads and thermal resistance.
- Excellent anti-oxidation and anti-corrosion properties thanks to the excellent behaviour of the calcium sulfonates, also in the presence of sea water.
- The **NEW GENERATION** of calcium sulfonate complex soap allows to keep outstanding **CERAN XM 460** performances even in case of high speed applications where normally polyurea or lithium complex greases are requested.
- **CERAN XM 460** does not contain lead, or other heavy metals considered harmful to human health and the environment.

TOTAL LUBRIFIANTS
INDUSTRIE
12-06-2018 (supersedes 01-08-2014)
CERAN XM 460
1/2



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.

| TYPICAL CHARACTERISTICS | METHODS | UNITS | CERAN XM 460 (typical values) |
|---------------------------------------------|----------------------------------------|-------------|----------------------------------|
| Soap/thickener | | - | Calcium sulfonate complex |
| NLGI grade | ASTM D 217/DIN 51 818 | - | 1-2 |
| Color | Visual | - | Light brown |
| Appearance | Visual | - | Smooth |
| Operating temperature range | | °C | - 25 to 180 |
| Kinematic viscosity of the base oil at 40°C | ASTM D 445/DIN 51 562-1/ISO 3104/ IP71 | mm²/s (cSt) | 460 |
| Mechanical stability | | | |
| Penetration at 25°C | ASTM D 217/DIN 51 818 | 0.1 mm | 280-310 |
| Penetration after 100 000 strokes | ISO 2137 | 0.1 mm | +6 |
| Shell Roller 100 hours at 80°C | ASTM D 1831 mod | 0.1 mm | +10 |
| Shell Roller 100 hours at 80°C + 10% water | ASTM D 1831 mod | 0.1 mm | -34 |
| Thermal stability | | | |
| Dropping point | IP 396 | °C | > 300 |
| Oil release 50 hours, 100 °C | ASTM D 6184 | % | 2.5 |
| Oil release 168 hours, 40°C | NF T 60-191 | % | 0.3 |
| Oxidation stability at 99°C +/-0.5°C | | | |
| Pressure drop after 100 hours | ASTM D 942 | Psi | 6 |
| Pressure drop after 500 hours | | Psi | 13 |
| Antirust properties | | | |
| EMCOR, distilled water | ISO 11007 | Rating | 0-0 |
| EMCOR, synthetic sea water | ISO 11007 | Rating | 0-0 |
| Copper corrosion, 24 hours at 100°C | ASTM D 4048 | Rating | 1b |
| Antiwear and EP properties | | | |
| Four ball wear (scar diameter) | ASTM D2266 | mm | 0.56 |
| Four ball weld load | ASTM D2596 | kgf | >400 |
| Cold properties | | | |
| Penetration at -20°C | ISO 13737 | 0.1 mm | 95 |
| Flow pressure at -20°C | DIN 51 805 | mbar | 1310 |
| Flow pressure at 1400 mbar | DIN 51 805 | °C | -25 |
| Torque at -20°C | | | |
| Starting torque | ASTM D 1478 | g.cm | 890 |
| After 1 hour | | g.cm | 72 |

Above characteristics are mean values given as an information.

TOTAL LUBRIFIANTS INDUSTRIE

12-06-2018 (supersedes 01-08-2014)

CERAN XM 460

2/2



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser www.quick-fds.com.